

# Hempel's Multicoat

## Product characteristics

### Description

Hempel's Multicoat is a high opacity semi-gloss topcoat and primer. Durable with good resistance to sunlight, water and oil. Can be used as a complete coating system.

### Recommended use

For use on glass fibre, wood and steel. For interior and exterior, use above the waterline.

### Features

- Not available.

## Product safety

**Flash point** 39°C [102°F]

### VOC content

Legislation	Value
EU	441 g/L [3.68 lb/US gal]

VOC values may vary with shade, please consult the Safety Data Sheet, section 9.

### Handling

Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Hempel's Safety Data Sheet for this product along with the Product Data Sheet.

## Product data

### Product code

51120

### Standard shade / code

White 10000 \*

### Gloss

Semi-gloss

### Volume solids

46 ± 2%

### Specific gravity

1.2 kg/L [10 lb/US gal]

### Reference dry film thickness

40 micron [1.6 mils]

## Surface preparation

### Cleanliness

- Remove oil, grease and other contaminants by suitable detergent cleaning.

### New build:

- Uncoated surface: Prepare bare substrates according to Hempel's primer instruction.

### Maintenance and Repair

- Previously coated surface: Abrade, clean and dry the surface.

## Application

### Thinner

Hempel's Thinner 811 0811  
Hempel's Thinner 808 08081

# Hempel's Multicoat

## Application method

Tool	Thinning max vol.	Application parameters
Brush	5%	Not Applicable.
Roller	5%	Not Applicable.
Paint Pad	5%	Not Applicable.

Keep thinning at an absolute minimum. The product can be applied by spray. Contact Hempel for more information.

## Film thickness

	Recommended
Dry film thickness	40 micron [1.6 mils]
Wet film thickness	90 micron [3.5 mils]
Theoretical spreading rate	11 m <sup>2</sup> /L [450 sq ft/US gal]

For best performance, avoid excessive film thickness.

## Application conditions

- To avoid condensation, apply on a clean and dry surface with a temperature that is at least 3°C [5°F] above the dew point.

## Relative Humidity:

- Relative humidity must be below 85% during drying and curing.

## Application remarks

- Stir well before use.
- Thinning of the topcoat may be required to ensure proper film formation. Thinning is limited to max. 5%.
- To use as a primer: Apply first coat of the product thinned with specified Hempel's Thinner: max 10%.
- To use as a topcoat: Apply 2-3 coats of the product.
- To obtain a smooth surface, sanding between coats is recommended (remove dust).

## Drying and overcoating

### Product compatibility

- Previous coat: Recommended products are: Hempel's Primer Undercoat
- Subsequent coat: None.

### Drying time

Surface temperature		10°C [50°F]	20°C [68°F]
Touch dry	hours	6	3
Ready to sand	hours	-	24

Determined for dry film thickness 40 micron [1.6 mils] at standard conditions, see Hempel's Explanatory Notes for details. Any masking tape used during paint application should be removed while the paint is still in the wet condition.

### Overcoating

Hempel's specification supersedes any guidelines indicated in the overcoating table

Quality name		10°C [50°F]	20°C [68°F]
Atmospheric medium			
Hempel's	Min	16 h	8 h
Multicoat	Max	5½ d	72 h

### Drying conditions

- To obtain the drying time stated, it is important to maintain sufficient ventilation during application, drying and curing.
- Condensation on the freshly applied coating should be avoided.

### Overcoating details

- If the maximum overcoating interval is exceeded, roughening of the surface is necessary to ensure intercoat adhesion.

### Other remarks

- The surface must be clean before overcoating.

# Hempel's Multicoat

## Storage

### Shelf life

Ambient temperature	25°C [77°F]
Product	60 months

Shelf life from date of production, when stored in original, unopened containers. Thereafter, the product quality must be re-inspected. Always check the best before date or expiry date on the label.

### Storage conditions

- Product must be stored according to local legislation, at 5°C [41°F] without direct sunlight and protected from rain and snow.

## Additional documents

Additional information is available at the Hempel website [hempel.com](http://hempel.com) or at your local Hempel website:

- Explanatory Notes explaining the fields in this Product Data Sheet.
- Surface Preparation Guidelines.
- Application Guidelines for different application methods.
- Further information: Hempel Yacht Paint Manual and [hempelyacht.com](http://hempelyacht.com)

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. Accordingly, the buyer/applicator should have regard to the PDS supplied together with the relevant batch of the Product (and not an earlier version). In addition to the PDS, the buyer/applicator may receive some or all of the following specifications, statements and/or guidelines as listed below or as are available from the Hempel website under 'Products' at [www.hempel.com](http://www.hempel.com) (the "Additional documents"):

No.	Document description	Location/comments
1.	Technical Statement	One-off specific advice provided on request for specific projects
2.	Specification	Only issued for specific projects
3.	PDS	This document
4.	Explanatory Notes to the PDS	Available at <a href="http://www.hempel.com">www.hempel.com</a> and contain relevant information about the Product testing parameters
5.	Application Instruction	Where available, at <a href="http://www.hempel.com">www.hempel.com</a>
6.	Generic technical guidelines (e.g. on application and surface preparation)	Where available, at <a href="http://www.hempel.com">www.hempel.com</a>

In the event of a conflict of information between the PDS and the Additional documents, the order of priority of information shall be in the order as set out above. In such event you should also contact your representative at Hempel for clarification. Furthermore, the buyer/applicator must have full regard to the relevant Safety Data Sheet provided with each Product and which can also be downloaded from [www.hempel.com](http://www.hempel.com).

Hempel shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements set out in the relevant PDS and the Additional Documents. The information and terms of this disclaimer apply to this PDS, the Additional documents and any other documents supplied by Hempel in respect of the Product. In addition, the Product is supplied and all technical assistance is given subject to Hempel's General Conditions of Sale, Delivery and Service, unless otherwise expressly agreed in writing.